



Norm: UNI EN 1676 e 1706

Numeric designation: EN AB and AC - 48100

Symbolic designation: EN AB and AC - AlSi17Cu4Mg

CHEMICAL COMPOSITION %

ALLOY DESIGNATION		ELEMENTS												
		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Other each	Other total
EN AB 48100 EN 1676:2020	Min	16,0	0	4,0	0	0,45	0	0	0	0	0	0	0	0
	Max	18,0	1,0	5,0	0,50	0,65	0,05	0,3	1,5	0,05	0,15	0,20	0,05	0,25
EN AC 48100 EN 1706:2020	Min	16,0	0	4,0	0	0,25	0	0	0	0	0	0	0	0
	Max	18,0	1,3	5,0	0,50	0,65	0,05	0,3	1,5	0,05	0,15	0,25	0,05	0,25

NOTE: Other each includes the limits of all elements unspecified in the grid.

MECHANICAL PROPERTIES

(Mechanical properties obtained from samples cast separately at +20°C room temperature)

CASTING PROCESS (condition)	TEMPER DESIGNATION	Rm	Rp02	A	HB	R Fatigue*
		Tensile strength	Yield strength	Elongation	Brinell hardness	Fatigue resistance
		EN 1706:2020	EN 1706:2020	EN 1706:2020	EN 1706:2020	EN 1706:2020
		MPa	MPa	%	HBW	MPa
INVESTMENT	F	200	180	1	90	60 - 90
INVESTMENT	T5	295	260	1	125	60 - 90

*Values for tests under rotating bending conditions up to 10⁷ cycles

PHYSICAL PROPERTIES

(The following properties are spoilt by the variation of the chemical composition, by its metallurgic structure, casting integrity and casting conditions, therefore these values are approximate)

SPECIFIC WEIGHT	2,79 Kg/dm ³	ELECTRICAL CONDUCTIVITY	EN 1706:2020	14 - 17 MS/m
SPECIFIC HEAT (at 100 °C)	0,91 J/gK	THERMAL CONDUCTIVITY	EN 1706:2020	120 - 130 W/(m K)
ELASTIC MODULUS	72 GPa	LINEAR THERMAL EXPANSION (20 °C - 100 °C)	EN 1706:2020	18·10 ⁻⁶ /K



Norm: UNI EN 1676 e 1706

Numeric designation: EN AB and AC - 48100

Symbolic designation: EN AB and AC - AlSi17Cu4Mg

TECHNOLOGICAL FEATURES
(Quality indications excerpted from the norm EN 1706:2020)

CASTABILITY	A	DECORATIVE ANODIZING	D
RESISTANCE TO HOT TEARING	C	ABILITY TO BE WELDED	D
PRESSURE TIGHTNESS	B	ABILITY TO BE POLISHED	D
MACHINABILITY (after cast)	E	STRENGTH AT ROOM TEMPERATURE	B
MACHINABILITY (after heat treatment)	B	STRENGTH AT ELEVATED TEMPERATURE (200°C)	B
RESISTANCE TO CORROSION	D	DUCTILITY	E

A: EXCELLENT, B: GOOD, C: FAIR, D: POOR, E: NOT RECOMMENDED, F: UNSUITABLE

GUIDELINES FOR USE

The ingot re-melting process must be carried out as fast as possible and overheating must be avoided (maximum melting temperature 780°C). Iron tools that may be touched by the liquid metal must be specially painted to avoid spoiling the alloy. The best alloy purification results are achieved by treating the alloy with inert gases, such as nitrogen and/or argon, to remove dissolved hydrogen and any oxides in the liquid bath. A careful skimming of the bath is recommended. It is allowed to recycle sprues and casting appendages up to 40% out of the total charge weight.

Heat Treatment - Alloy not to be treated.

FURTHER FEATURES OF THE ALLOY

Resistance to weathering and seawater - Limited resistance to weathering and corrosion in general; not suitable for applications directly touched by seawater.

Notes - Castability is excellent and makes it possible to use it a lot. The higher the content of Mg is, the more this alloy tends to hot tearing, even if this tendency is not well-defined.

USUAL APPLICATIONS

This is a hypereutectic AlSi alloy with high wear resistance and excellent mechanical properties, even at higher temperatures. It is used to produce castings under extreme wear conditions; multi-cylinder engine heads for the automotive and shipbuilding industries.

This alloy **does not comply** with Standard EN 601.